

Piocel Adhesives/Coatings for Optical Devices are highly specialized optically clear adhesives offering excellent optical properties and adhesion to various types of transparent substrates. Piocel Adhesives/Coatings are 100% solids and cure in seconds upon exposure to UV light.

DESCRIPTION

Piocel offers wide range of UV light curing adhesives/coatings for variety of applications for bonding, coating, encapsulating, and sealing.

Piocel Adhesives/Coatings has rapid cure property, non-yellowing, thermal resistance, high oxidative and hydrolytic (moisture) stability, which are required by optical devices industry applications, displays, touch panels and others requiring an optically clear bond.

FEATURE and BENEFIT

- Silicone Epoxy copolymer
- Heat resistance
- Rapid UV curable / one component system
- Excellent boiling water resistance
- Good impact resistance

PROPERTIES

LIQUID PROPERTIES:

Appearance	-	transparent
Refractive Index	@589nm	1.50 ± 0.01
Viscosity	cPs @25°C	200 ~ 400
Solid Contents	%	82

※ Dilution solvent

-. MEK (Methyl ethyl ketone) : CAS# 78-93-3

CURED PROPERTIES:

Refractive Index	@589nm	1.51 ± 0.01
Pencil Hardness	500g load / CPI film coating (10μm Coated)	7H

HOW TO USE

1. Carefully clean and dry all surfaces to be coated.
2. Apply the coating solution to the prepared surfaces.
Dry to remove the dilution solvent **at 110°C for 2min.**
3. UV Curing Condition.
Minimum UV dose of this product for complete cure is **2,000 mJ/cm² under a nitrogen environment.**
However, the minimum dosage is dependent upon the thickness of the coating layer.
4. Post Thermal Curing Condition.
It is recommended for complete post thermal curing that need about **6 hrs at 80°C** may be necessary.

GENERAL INFORMATION

The required intensity and cure time should be determined during the initial process validation stage. Factors that should be considered during process validation which can affect the adhesive cure rate and depth of cure include, but are not limited to, the part geometry, bond-gap size, percent light transmission through the substrate, distance from the light source to the adhesive/coating area, UV light intensity and spectral output of the light source, the desired margin of safety to be built into the process, and minimum and maximum exposure times.

For safe handling information on this product, consult the Safety Data Sheet, SDS.

STORAGE

Products should be stored unopened in dry place out of direct sunlight. **Products should be kept at room temperature (20~25°C) away from direct light.** Protect from extreme heat or cold, do not refrigerate.